Honeywell Docket No.: 30-5080

CLAIMS

What is claimed is:

- 1. An adhesion promoter comprising:
 - a polymeric strand with an epoxy-reactive group other than a phenolic hydroxyl group and further comprising a crosslinking group;
 - wherein the crosslinking group is capable of crosslinking the polymeric strand with a rubber in a crosslinking reaction; and

wherein the polymeric strand is water soluble in an amount of no less than 10g/l.

- 2. The adhesion promoter of claim 1 wherein the polymeric strand comprises an organic polymer.
- The adhesion promoter of claim 2 wherein the organic polymer comprises polybutadiene. 3.
- The adhesion promoter of claim 3 wherein the polybutadiene is grafted with a maleic an-4. hydride, and wherein the maleic anhydride is reacted with a compound selected from the group consisting of a methoxy polyethylene glycol, a monoamine terminated polyoxyalkylene, and a monoalcohol terminated polyoxyalkylene.
- The adhesion promoter of claim 1 further comprising a second polymer. 5.
- The adhesion promoter of claim 5 wherein the second polymer comprises a styrene-buta-6. diene-vinylpyridine terpolymer.
- The adhesion promoter of claim 1 wherein the epoxy-reactive group is a carboxylic acid 7. group.
- The adhesion promoter of claim 1 wherein the crosslinking group is in the backbone of the 8. polymeric strand.
- The adhesion promoter of claim 8 wherein the crosslinking group comprises a double bond. 9.
- The adhesion promoter of claim 1 wherein the crosslinking reaction comprises formation of 10. a covalent bond with a sulfur atom.

Honeywell Docket No.: 30-5080

- 11. The adhesion promoter of claim 1 wherein the crosslinking reaction comprises a reaction selected from the group consisting of a nucleophilic addition, an electrophilic addition, and a cyclo addition.
- 12. The adhesion promoter of claim 1 wherein the rubber is at least one of a synthetic rubber and a natural rubber.
- 13. The adhesion promoter of claim 6 wherein the rubber further comprises polybutadiene grafted with maleic anhydride.
- 14. A rubber containing product comprising:
 - a polymeric fiber coated with a compound having a plurality of epoxy groups, wherein the polymeric fiber is coupled to a rubber via an adhesion promoter;
 - wherein the adhesion promoter comprises a polymeric strand with an epoxy-reactive group other than a phenolic hydroxyl group, and further comprises a crosslinking group that has crosslinked the polymeric strand with the rubber; and wherein the adhesion promoter is water soluble in an amount of at least 10g/l.
- 15. The rubber containing product of claim 14 wherein the polymeric fiber comprises a polyester fiber, the polymeric strand comprises maleinized polybutadiene derivatized with methoxy polyethylene glycol, the epoxy-reactive group comprises a carboxylic acid group, and wherein the crosslinking group comprises a double bond.
- 16. The rubber containing product of claim 14 wherein the polymeric fiber comprises a polyester fiber, the polymeric strand comprises maleinized polybutadiene derivatized with a monoamine terminated poly(ethylene oxide-propylene oxide) copolymer, the epoxy-reactive group comprises a carboxylic acid group, and wherein the crosslinking group comprises a double bond.

Honeywell Docket No.: 30-5080

17. The rubber containing product of claim 14 further comprising a styrene-butadiene-vinylpyridine terpolymer, wherein at least a portion of the styrene-butadiene-vinylpyridine terpolymer is coupled to the rubber.

- 18. A method of fabricating a rubber containing product, comprising:

 providing a rubber, and a polymeric fiber comprising a plurality of epoxy groups;

 providing an adhesion promoter having a polymeric strand with an epoxy-reactive group

 other than a phenolic hydroxyl group, and further having a crosslinking group, and

 wherein the adhesion promoter is water soluble in an amount of at least 10g/l;

 covalently coupling the rubber with the polymeric fiber via the adhesion promoter, wherein

 the epoxy-reactive group forms a covalent bond with the epoxy group, and wherein

 the crosslinking group forms another covalent bond with the rubber.
- 19. The method of claim 18 wherein the adhesion promoter comprises a maleinized polybutadiene derivatized with methoxy polyethylene glycol.
- 20. The method of claim 18 wherein the adhesion promoter comprises a maleinized polybutadiene derivatized with monoamine terminated poly(ethylene oxide-propylene oxide) copolymer.
- 21. The method of claim 18 further comprising providing a styrene-butadiene-vinylpyridine terpolymer and coupling at least a portion of the styrene-butadiene-vinylpyridine latex to the adhesion promoter.
- 22. The method of claim 21 further comprising admixing a maleinized polybutadiene with the rubber.